

RO4400™ Series Bondply

Data Sheet


RO4450B™ and RO4450F™ Bondply

RO4000® dielectric materials have long been used in combination with FR-4 cores and bondplys as a means to achieve a performance upgrade of standard FR-4 multi-layer designs. RO4003C™, RO4350B™, and RO4000 LoPro™ glass reinforced hydrocarbon/ceramic laminates have been used in layers where operating frequency, dielectric constant, or high-speed signal requirements dictate the need for high performance materials. FR-4 cores and bondply are still commonly used to inexpensively form less critical signal layers.

The RO4400™ bondply family is comprised of three grades based on the RO4000 series core materials, and are compatible in multi-layer constructions with either RO4003C, RO4350B or RO4000 LoPro laminates. A high post-cure Tg (>280°C / >536°F) makes RO4400 series bondply an excellent choice for multi-layers requiring sequential laminations as fully cured RO4400 bondplys are capable of handling multiple lamination cycles. In addition, FR-4 compatible bond requirements (177°C/350°F) permit RO4400 bondply and low flow FR-4 bondply to be combined into non-homogeneous multi-layer constructions using a single bond cycle.

RO4450F™ bondply has demonstrated improvement in lateral flow capability, and is becoming the first choice for new designs or as a replacement in designs that have difficult fill requirements.

Each of the RO4450B and RO4450F bondplys are recognized by Underwriter Laboratories with the UL-94 flame rating, and are compatible with lead-free processes.



Typical Values

RO4450B and RO4450F Bondply

PROPERTY	TYPICAL VALUES			DIRECTION	UNITS	CONDITION	TEST METHOD
	RO4450B	RO4450F					
Thickness	3.6 (0.091)	4 (0.101)	4 (0.101)	Z	mils (mm)	-	-
Dielectric Constant, ϵ_r	3.30 ± 0.05	3.54 ± 0.05	3.52 ± 0.05	Z	-	10GHz - 23°C	IPC-TM-650 2.5.5.5
Dissipation Factor, tan δ	0.004	0.004	0.004	Z	-	10GHz-23°C	IPC-TM-650 2.5.5.5
Dielectric Strength	1000	1000	1000	Z	V/mil	23°C/50% RH	IPC-TM-650 2.5.6
Volume Resistivity	9.26 X 10 ⁷	9.26 X 10 ⁷	8.93 X 10 ⁸	-	MΩ•cm	23°C/50% RH	IPC-TM-650 2.5.17.1
Surface Resistivity	3.82 X 10 ⁷	3.82 X 10 ⁷	1.03 X 10 ⁷	X,Y	MΩ	23°C/50% RH	IPC-TM-650 2.5.17.1
Thermal Conductivity	0.60	0.60	0.65	Z	W/m/K	80°C	ASTM C518
Moisture Absorption	0.010	0.05	0.09	-	%	48 hrs immersion 0.060" sample temperature 50°C	ASTM D570
Tg	>280	>280	>280	-	°C TMA	-60°C - 300°C @ 10°C/min	IPC-TM-650 2.4.24
Td	390	390	390	-	°C TGA		ASTM D3850
Density	1.80	1.86	1.83	-	gm/cm ³	23°C	ASTM D792
Copper Adhesion	4.0 (0.70)	4.9 (0.86)	4.0 (0.70)	Z	pli (N/mm)	½ oz. EDC After Solder Float	IPC-TM-650 2.4.8
Coefficient of Thermal Expansion	19 17 60	19 17 50	19 17 50	X Y Z	ppm/°C	-55 to 280°C	IPC-TM-650 2.4.41
Color	White	White	White	-	-	-	-
Flammability	V-0	V-0	V-0				UL94
Lead-Free Process Compatible	Yes	Yes	Yes				

Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

Rogers UL file number is E102763B.

STANDARD THICKNESS:	STANDARD SIZE:
RO4450B, 0.0036" (0.091mm), 0.004", (0.101mm) RO4450F 0.0040" (0.101mm)	24X18" Sheets (610mm X 457mm) Contact Customer Service for other available sizes.

The information contained in this data sheet and processing guide is intended to assist you in designing with Rogers' circuit materials and prepreg. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet and processing guide will be achieved by a user for a particular purpose. The user is responsible for determining the suitability of Rogers' circuit materials and prepreg for each application.

Prolonged exposure in an oxidative environment may cause changes to the dielectric properties of hydrocarbon based materials. The rate of change increases at higher temperatures and is highly dependent on the circuit design. Although Rogers' high frequency materials have been used successfully in innumerable applications and reports of oxidation resulting in performance problems are extremely rare, Rogers recommends that the customer evaluate each material and design combination to determine fitness for use over the entire life of the end product.

These commodities, technology and software are exported from the United States in accordance with the Export Administration regulations. Diversion contrary to U.S. law prohibited.

The Rogers' logo, RO4000, RO4400, RO4003C, RO4350B, RO4450B, RO4450F and LoPro are licensed trademarks of Rogers Corporation or one of its subsidiaries.
© 2015 Rogers Corporation, Printed in U.S.A, All rights reserved.
Revised 1197 060515 Publication #92-150