

## TMM<sup>®</sup> Thermoset Microwave Materials



TMM<sup>®</sup> thermoset microwave materials are ceramic, hydrocarbon, thermoset polymer composites designed for high plated-thru-hole reliability stripline and microstrip applications. TMM laminates are available in a wide range of dielectric constants and claddings.

The electrical and mechanical properties of TMM laminates combine many of the benefits of both ceramic and traditional PTFE microwave circuit laminates, without requiring the specialized production techniques common to these materials. TMM laminates do not require a sodium naphthate treatment prior to electroless plating.

TMM laminates have an exceptionally low thermal coefficient of dielectric constant, typically less than 30 ppm/°C. The material's isotropic coefficients of thermal expansion, very closely matched to copper, allow for production of high reliability plated through holes, and low etch shrinkage values. Furthermore, the thermal conductivity of TMM laminates is approximately twice that of traditional PTFE/ceramic laminates, facilitating heat removal.

TMM laminates are based on thermoset resins, and do not soften when heated. As a result, wire bonding of component leads to circuit traces can be performed without concerns of pad lifting or substrate deformation.

TMM laminates combine many of the desirable features of ceramic substrates with the ease of soft substrate processing techniques. TMM laminates are available clad with 1/2 oz/ft<sup>2</sup> to 2 oz/ft<sup>2</sup> electrodeposited copper foil, or bonded directly to brass or aluminum plates. Substrate thicknesses of 0.015" to 0.500" are available. The base substrate is resistant to etchants and solvents used in printed circuit production. Consequently, all common PWB processes can be used to produce TMM thermoset microwave materials.

### Data Sheet



#### FEATURES AND BENEFITS:

- Wide range of dielectric constants
  - Ideal for single material systems on a wide variety of applications
- Exceptional mechanical properties
  - Resist creep and cold flow
- Coefficient of thermal expansion matched to copper
  - High reliability of plated through holes
- Resistant to process chemicals
  - Reduces damage to material during fabrication and assembly processes
- Thermoset resin
  - Reliable wirebonding
  - No specialized production techniques required
  - TMM10 and 10i laminates can replace alumina substrates

#### SOME TYPICAL APPLICATIONS:

- RF and microwave circuitry
- Power amplifiers and combiners
- Filters and coupler
- Satellite communication systems
- Global Positioning Systems Antennas
- Patch Antennas
- Dielectric polarizers and lenses
- Chip testers

PROPERTY	TYPICAL VALUES						DIRECTION	UNITS	CONDITIONS	TEST METHOD
	TMM3	TMM4	TMM6	TMM10	TMM10i	TMM13i				
<sup>(4)</sup> Dielectric Constant, $\epsilon_r$ Process	3.27 ± 0.032	4.50 ± 0.045	6.00 ± 0.080	9.20 ± 0.230	9.80 ± 0.245	<sup>(3)</sup> 12.85 ± 0.35	Z		10 GHz	IPC-TM-650 method 2.5.5.5
<sup>(2)</sup> Dielectric Constant, $\epsilon_r$ Design	3.45	4.70	6.3	9.8	9.9	12.2			8 GHz - 40 GHz	Differential Phase Length Method
<sup>(4)</sup> Dissipation Factor, $\tan \delta$	0.0020	0.0020	0.0023	0.0022	0.0020	0.0019	Z		10 GHz	IPC-TM-650 method 2.5.5.5
Thermal Coefficient of $\epsilon_r$	+37	+15	-11	-38	-43*	-70		ppm/°K	-55 to +125°C	IPC-TM-650 method 2.5.5.5
Insulation Resistance	>2000	>2000	>2000	>2000	>2000	>2000		Gohm	C/96/60/95	ASTM D257
Volume Resistivity	3X10 <sup>9</sup>	6X10 <sup>8</sup>	1X10 <sup>8</sup>	2X10 <sup>8</sup>	2X10 <sup>8</sup>	-		Mohm cm		ASTM D257
Surface Resistivity	>9X10 <sup>9</sup>	1X10 <sup>9</sup>	1X10 <sup>9</sup>	4X10 <sup>7</sup>	4X10 <sup>7</sup>	-		Mohm		ASTM D257
Flexural Strength	16.53	15.91	15.02	13.62	-	-	X,Y	kpsi	A	ASTM D790
Flexural Modulus	1.72	1.76	1.75	1.79	1.80*		X,Y	Mpsi	A	ASTM D790
Water Absorption (2X2)	1.27mm (0.050")	0.06	0.07	0.06	0.09	0.16		%	D/24/23	ASTM D570
	3.18mm (0.125")	0.12	0.18	0.20	0.20	0.13	0.13			
Specific Gravity	1.78	2.07	2.37	2.77	2.77	3.0			A	ASTM D792
Specific Heat	0.87	0.83	0.78	0.74	0.72*	-		J/g/K	A	Calculated
Thermal Conductivity	0.70	0.70	0.72	0.76	0.76	-	Z	W/m/K	80°C	ASTM C518
Coefficient of Thermal Expansion	15	16	18	21	19	19	X,Y	ppm/K	0 to 140°C	ASTM E 831 IPC-TM-650, 2.4.41
	23	21	26	20	20	20	Z			
Td	425	425	425	425	425	425		°C TGA		ASTM D3850
Copper Peel Strength	5.7 (1.0)	5.7 (1.0)	5.7 (1.0)	5.0 (0.9)	5.0 (0.9)	4.0 (0.7)	X,Y	lb/inch (N/mm)	after solder float 1 oz. EDC	IPC-TM-650 Method 2.4.8
Lead-Free Process Compatible	YES	YES	YES	YES	YES	YES				

Notes: ASTM E831 corresponds to IPC-TM-650, method 2.4.41  
\* estimated

Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

- (1) Prolonged exposure in an oxidative environment may cause changes to the dielectric properties of hydrocarbon based materials. The rate of change increases at higher temperatures and is highly dependent on the circuit design. Although Rogers' high frequency materials have been used successfully in innumerable applications and reports of oxidation resulting in performance problems are extremely rare, Rogers recommends that the customer evaluate each material and design combination to determine fitness for use over the entire life of the end product.
- (2) The design DK is an average number from several different tested lots of material and on the most common thickness/s. If more detailed information is required, please contact Rogers Corporation. Refer to Rogers Technical paper "Dielectric Properties of High Frequency Materials" available on [www.rogerscorp.com/acm](http://www.rogerscorp.com/acm).
- (3) Method 2.5.5.6.

Standard Thickness	Standard Panel Size	Standard Copper Cladding
0.015" (0.381mm), 0.020" (0.508mm), 0.025" (0.635mm), 0.030" (0.762mm), 0.050" (1.270mm), 0.060" (1.524mm), 0.075" (1.905mm), 0.100" (2.540mm), 0.125" (3.175mm), 0.150" (3.810mm), 0.200" (5.080mm), 0.250" (6.350mm), 0.275" (6.985mm), 0.300" (7.620mm), 0.500" (12.70mm)	18" X 12" (457 X 305mm) 18" X 24" (457 X 610mm)	½ (17µm), 1 oz (35µm), 2 oz. (70µm) electrodeposited copper foil.  Heavy metal cladding available. Contact Rogers customer service.

The information in this data sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application.

TMM is a licensed trademark of Rogers Corporation.  
The Rogers' logo is a licensed trademark of Rogers Corporation.  
© 2015 Rogers Corporation, Printed in U.S.A., All rights reserved. Revised: 1106 021015 Publication #92-108